

IN THE CLAIMS:

1. (Previously Amended) A resin cushion article having a spring structure, comprising a three-dimensional structure with voids and a predetermined bulk density, said three-dimensional structure being formed by contacting, entwining, and gathering adjacent ones of random loops or curls of solid and/or hollow continuous filaments and/or short filaments made from a mixture of a polyolefin resin and vinyl acetate resin, ethylene vinyl acetate copolymer or styrene butadiene styrene, wherein said three-dimensional structure is increased in bulk density across its width at predetermined intervals in a direction of its length and wherein said article has a uniform thickness.

2. (Currently Amended) The resin molded article according to claim 1, wherein said three-dimensional structure has voids providing each portions of low and high bulk densities.

3. (Previously Amended) The resin molded article according to claim 1, a mixture ratio of said polyolefin resin to said vinyl acetate resin or said ethylene vinyl acetate copolymer is 70 to 97 wt% to 3 to 30 wt%.

4. (Previously Amended) The resin molded article according to claim 2, a mixture ratio of said polyolefin resin to said vinyl acetate resin or said ethylene vinyl acetate copolymer is 70 to 97 wt% to 3 to 30 wt%.

5. (Previously Amended) The resin molded article according to claim 1, a mixture

ratio of said polyolefin resin to said vinyl acetate resin or said ethylene vinyl acetate copolymer is 80 to 90 wt% to 10 to 20 wt%.

6. (Previously Amended) The resin molded article according to claim 2, a mixture ratio of said polyolefin resin to said vinyl acetate resin or said ethylene vinyl acetate copolymer is 80 to 90 wt% to 10 to 20 wt%.

7. (Previously Amended) The resin molded article according to claim 1, wherein a mixture ratio of said polyolefin resin to said styrene butadiene styrene is 50 to 97 wt% to 3 to 50 wt%.

8. (Previously Amended) The resin molded article according to claim 2, wherein a mixture ratio of said polyolefin resin to said styrene butadiene styrene is 50 to 97 wt% to 3 to 50 wt%.

9. (Canceled)

10. (Previously Amended) The resin molded article according to claim 1, wherein a mixture ratio of said polyolefin resin to said styrene butadiene styrene is 70 to 90 wt% to 10 to 30 wt%.

11. (Previously Amended) The resin molded article according to claim 2, wherein a

mixture ratio of said polyolefin resin to said styrene butadiene styrene is 70 to 90 wt% to 10 to 30 wt%.

12. (Canceled)

13. (Previously Amended) The resin molded article according to claim 1, wherein said solid continuous filaments and/or short filaments have a diameter of 0.3 mm to 3.0 mm, and said hollow continuous filaments have a diameter of 1.0 mm to 3.0 mm.

14. (Previously Amended) The resin molded article according to claim 2, wherein said solid continuous filaments and/or short filaments have a diameter of 0.3 mm to 3.0 mm, and said hollow continuous filaments have a diameter of 1.0 mm to 3.0 mm.

15. (Previously Amended) The resin molded article according to claim 1, wherein said solid continuous filaments and/or short filaments have a diameter of 0.7 to 1.0 mm, and said hollow continuous filaments have a diameter of 1.5 mm to 2.0 mm.

16. (Previously Amended) The resin molded article according to claim 2, wherein said solid continuous filaments and/or short filaments have a diameter of 0.7 to 1.0 mm, and said hollow continuous filaments have a diameter of 1.5 mm to 2.0 mm.

17. (Original) The resin molded article according to claim 1, wherein said three-

dimensional structure has a bulk density of 0.001 to 0.08 g/cm³.

18. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure has a bulk density of 0.001 to 0.08 g/cm³.

19. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure has a bulk density of 0.001 to 0.08 g/cm³.

20. (Original) The resin molded article according to claim 4, wherein said three-dimensional structure has a bulk density of 0.001 to 0.08 g/cm³.

21. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure has a bulk density of 0.001 to 0.08 g/cm³.

22. (Original) The resin molded article according to claim 1, wherein said three-dimensional structure has a bulk density of 0.02 to 0.06 g/cm³.

23. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure has a bulk density of 0.02 to 0.06 g/cm³.

24. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure has a bulk density of 0.02 to 0.06 g/cm³.

25. (Original) The resin molded article according to any one of claim 4, wherein said three-dimensional structure has a bulk density of 0.02 to 0.06 g/cm³.

26. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure has a bulk density of 0.02 to 0.06 g/cm³.

27. (Original) The resin molded article according to claim 1, wherein said three-dimensional structure is a cushion material for seats of an automotive vehicle or a bed.

28. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure is a cushion material for seats of an automotive vehicle or a bed.

29. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure is a cushion material for seats of an automotive vehicle or a bed.

30. (Original) The resin molded article according to claim 4, wherein said three-dimensional structure is a cushion material for seats of an automotive vehicle or a bed

31. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure is a cushion material for seats of an automotive vehicle or a bed

32. (Original) The resin molded article according to claim 6, wherein said three-

dimensional structure is a cushion material for seats of an automotive vehicle or a bed.

33. (Canceled)

34. (Original) The resin molded article according to claim 1, wherein said three-dimensional structure has a bulk density of 0.005 to 0.03 g/cm³ at low density portions, and a bulk density of 0.03 to 0.08 g/cm³ at high density portions

35. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure has a bulk density of 0.005 to 0.03 g/cm³ at low density portions, and a bulk density of 0.03 to 0.08g/cm³ at high density portions

36. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure has a bulk density of 0.005 to 0.03 g/cm³ at low density portions, and a bulk density of 0.03 to 0.08 g/cm³ at high density portions

37. (Original) The resin molded article according to claim 4, wherein said three-dimensional structure has a bulk density of 0.005 to 0.03 g/cm³ at low density portions, and a bulk density of 0.03 to 0.08 g/cm³ at high density portions

38. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure has a bulk density of 0.005 to 0.03 g/cm³ at low density portions, and a

bulk density of 0.03 to 0.08 g/cm³ at high density portions.

39. (Original) The resin molded article according to claim 1, wherein said three-dimensional structure has a bulk density of 0.008 to 0.03 g/cm³ at low density portions, and a bulk density of 0.04 to 0.07 g/cm³ at high density portions,

40. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure has a bulk density of 0.008 to 0.03 g/cm³ at low density portions, and a bulk density of 0.04 to 0.07 g/cm³ at high density portions

41. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure has a bulk density of 0.008 to 0.03 g/cm³ at low density portions, and a bulk density of 0.04 to 0.07 g/cm³ at high density portions.

42. (Original) The resin molded article according to claim 4, wherein said three-dimensional structure has a bulk density of 0.008 to 0.03 g/cm³ at low density portions, and a bulk density of 0.04 to 0.07 g/cm³ at high density portions

43. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure has a bulk density of 0.008 to 0.03 g/cm³ at low density portions, and a bulk density of 0.04 to 0.07 g/cm³ at high density portions

44. (Original) The resin molded article according to claim 1, wherein said three-dimensional structure has a bulk density of 0.01 to 0.03 g/cm³ at low density portions, and a bulk density of 0.05 to 0.06 g/cm³ at high density portions

45. (Original) The resin molded article according to claim 2, wherein said three-dimensional structure has a bulk density of 0.01 to 0.003 g/cm³ at low density portions, and a bulk density of 0.05 to 0.06 g/cm³ at high density portions.

46. (Original) The resin molded article according to claim 3, wherein said three-dimensional structure has a bulk density of 0.01 to 0.03 g/cm³ at low density portions, and a bulk density of 0.05 to 0.06 g/cm³ at high density portions.

47. (Original) The resin molded article according to claim 4, wherein said hollow filaments are covered with solid filaments three-dimensional structure has a bulk density of 0.01 to 0.03 g/cm³ at low density portions, and a bulk density of 0.05 to 0.06 g/cm³ at high density portions.

48. (Original) The resin molded article according to claim 5, wherein said three-dimensional structure has a bulk density of 0.01 to 0.03 g/cm³ at low density portions, and a bulk density of 0.05 to 0.06 g/cm³ at high density portions.

49 . (Currently Amended) The resin molded article according to claim 9 3, wherein

said three-dimensional structure has a void ratio of 96 to 99 %, at said low density portions, and a void ratio of 91 to 97 % at said high density portions

50. (Currently Amended) The resin molded article according to claim 9 3, wherein said three-dimensional structure has a void ratio of 97 to 99 % at said low density and a void ratio of preferably 92 to 96 % at said high density portions ~~portions~~.

51. (Currently Amended) The resin molded article according to claim 9 3, wherein said three-dimensional structure has a void ratio of 97 to 98 % at said low density portions, and a void ratio of 93 to 94 % at said high density portions.

52. (Original) The resin molded article according to claim 1, wherein a mixture ratio of solid filaments to hollow filaments is 0 to 50 to 50 to 100.

53. (Original) The resin molded article according to claim 2, wherein a mixture ratio of solid filaments to hollow filaments is 0 to 50 to 50 to 100.

54. (Original) The resin molded article according to claim 3, wherein a mixture ratio of solid filaments to hollow filaments is 0 to 50 to 50 to 100.

55. (Original) The resin molded article according to claim 4, wherein a mixturc ratio of solid filaments to hollow filaments is 0 to 50 to 50 to 100.

56. (Original) The resin molded article according to claim 5, wherein a mixture ratio of solid filaments to hollow filaments is 0 to 50 to 50 to 100.

57. (Original) The resin molded article according to claim 1, wherein outer surfaces of said hollow filaments are covered with solid filaments.

58. (Original) The resin molded article according to claim 2, wherein outer surfaces of said hollow filaments are covered with solid filaments.

59. (Original) The resin molded article according to claim 3, wherein outer surfaces of said hollow filaments are covered with solid filaments.

60. (Original) The resin molded article according to claim 4, wherein outer surfaces of said hollow filaments are covered with solid filaments

61. (Original) The resin molded article according to claim 5, wherein outer surfaces of said hollow filaments are covered with solid filaments.

62. (Previously Added) The resin molded article according to claim 1, wherein a take-off speed for taking off the extruded continuous filaments is changed to thereby form high density portions having an increased bulk density which each extend in a direction of width of said three-dimensional structure and are arranged at appropriate space intervals in a

direction of length of said three-dimensional structure.